



## acoustic absorption

	Limestone White Ref : 001BC	Granite Grey Ref : 002GG	Slate Blue Ref : 003BA
			
absorption range	D	E	E
aw (MH)	0.30	0.25	0.25

Frequency octave band	Acoustic absorption coefficient		
	125	0.05	0.05
250	0.05	0.05	0.05
500 *	0.25	0.20	0.20
1000 *	1.00	1.00	1.00
2000 *	1.00	1.00	1.00
4000	0.90	0.80	0.80

\* Acoustic frequencies from 500 to 2000 Hz correspond to human voices frequencies.

Sound absorption coefficient curve in accordance with standard NF EN ISO 354